



IN THE CLAIMS:

1. (Cancelled)

2. (Currently Amended) The primer composition according to claim [[1]] 3 which has a content of the organic solvent (II) of from 100 to 4000 parts by weight based on 100 parts by weight of the modified copolymer (I).

3. (New) A primer composition comprising:

(I) a modified copolymer obtained by addition of a polar group represented by the following formula (1) or (2)



wherein in the formulas (1) and (2), R^1 is hydrogen or an alkyl group of 1 to 6 carbon atoms, to at least one (co)polymer selected from the group consisting of

- (A) an olefin (co)polymer,
- (B) a halogenated olefin (co)polymer
- (C) a styrene/conjugated diene/styrene tri-block copolymer or its hydrogenated product and

(D) a halogenated styrene/conjugated diene/styrene tri-block copolymer or its hydrogenated product,

wherein the modified copolymer contains the polar group in an amount of from 1×10^{-3} to 250×10^{-3} mol based on 100 g of the modified copolymer, and

(II) an organic solvent.

4. (New) The primer composition according to claim 3, wherein the modified copolymer (I) is obtained by modifying a maleic anhydric-grafted copolymer with diethylene glycol.

5. (New) The primer composition according to claim 4, wherein the maleic anhydride-grafted copolymer is maleic anhydride-grafted propylene/ethylene copolymer.